

Subfolder	Recipe	Surface Treatment	Treatment Durat.[min]	Wait Press. [mbar]	Film 1		Film 2		Film 3		Film 4	
					Step	pocket	Step	pocket	Step	pocket	Step	pocket
250mm	250_[Ar-1]_Cr_160	Ar plasma	1	8.0E-07	250_Cr_16.0	2						
250mm	250_Ag_160	None		8.0E-07	250_Ag_16.0	3						
250mm	250_Al_160	None		1.0E-06	250_Al_16.0	1						
250mm	250_Al-Cr_160	None		8.0E-07	250_Al_16.0	1	250_Cr_16.0	2				
250mm	250_Al-Ti_160	None		1.0E-06	250_Al_16.0	1	250_Ti_16.0	5				
250mm	250_Al-Ti-Au-Ti_160	None		1.0E-06	250_Al_16.0	1	250_Ti_16.0	5	250_Au_16.0	3	250_Ti_16.0	5
250mm	250_Au_160	None		2.0E-06	250_Au_16.0	3						
250mm	250_Co_160	None		1.0E-06	250_Co_16.0	4						
250mm	250_Cr_160	None		8.0E-07	250_Cr_16.0	2						
250mm	250_Cr-Ag_160	None		8.0E-07	250_Cr_16.0	2	250_Ag_16.0	3				
250mm	250_Cr-Al_160	None		8.0E-07	250_Cr_16.0	2	250_Al_16.0	1				
250mm	250_Cr-Au_160	None		8.0E-07	250_Cr_16.0	2	250_Au_16.0	3				
250mm	250_Cr-Co_160	None		1.0E-06	250_Cr_16.0	2	250_Co_16.0	4				
250mm	250_Cr-Cu_160	None		8.0E-07	250_Cr_16.0	2	250_Cu_16.0	4				
250mm	250_Cr-Pt_160	None		8.0E-07	250_Cr_16.0	2	250_Pt_16.0	6				
250mm	250_Cu_160	None		1.0E-06	250_Cu_16.0	4						
250mm	250_Pt_160	None		2.0E-06	250_Pt_16.0	6						
250mm	250_Ti_160	None		8.0E-07	250_Ti_16.0	5						
250mm	250_Ti-Al_160	None		8.0E-07	250_Ti_16.0	5	250_Al_16.0	1				
250mm	250_Ti-Au_160	None		8.0E-07	250_Ti_16.0	5	250_Au_16.0	3				
250mm	250_Ti-Au-Ti_160	None		8.0E-07	250_Ti_16.0	5	250_Au_16.0	3	250_Ti_16.0	5		
250mm	250_Ti-Pt_160	None		8.0E-07	250_Ti_16.0	5	250_Pt_16.0	6				
350mm	350_[O2]_Ti-Pt-Ti_80	O2 plasma	1	8.0E-07	350_Ti_8.0	5	350_Pt_8.0	6	350_Ti_8.0	5		
350mm	350_Ag_80	None		1.0E-06	350_Ag_8.0	3						
350mm	350_Al_80	None		1.0E-06	350_Al_8.0	1						
350mm	350_Au_50	None		2.0E-06	350_Au_5.0	3						
350mm	350_Au_80	None		2.0E-06	350_Au_8.0	3						
350mm	350_Au_100_wait-12h	None		8.0E-07	Wait 12h		350_Au_10.0	3				
350mm	350_Co_80	None		1.0E-06	350_Co_8.0	4						
350mm	350_Cr_80	None		8.0E-07	350_Cr_8.0	2						
350mm	350_Cr-Ag_80	None		8.0E-07	350_Cr_8.0	2	350_Ag_8.0	3				
350mm	350_Cr-Al_80	None		8.0E-07	350_Cr_8.0	2	350_Al_8.0	1				
350mm	350_Cr-Au_03-10	None		8.0E-07	350_Cr_0.3	2	350_Au_1.0	3				
350mm	350_Cr-Au_50	None		8.0E-07	350_Cr_5.0	2	350_Au_5.0	3				
350mm	350_Cr-Au_80	None		8.0E-07	350_Cr_8.0	2	350_Au_8.0	3				
350mm	350_Cr-Au_80-100_wait-12h	None		8.0E-07	Wait 12h		350_Cr_8.0	2	350_Au_10.0	3		
350mm	350_Cr-Co_80	None		1.0E-06	350_Cr_8.0	2	350_Co_8.0	4				
350mm	350_Cr-Cu_80	None		8.0E-07	350_Cr_8.0	2	350_Cu_8.0	4				
350mm	350_Cr-Pt_80	None		8.0E-07	350_Cr_8.0	2	350_Pt_8.0	6				
350mm	350_Cu_80	None		1.0E-06	350_Cu_8.0	4						
350mm	350_Pt_80	None		2.0E-06	350_Pt_8.0	6						
350mm	350_Ti_80	None		8.0E-07	350_Ti_8.0	5						
350mm	350_Ti-Au_80-100_wait-12h	None		8.0E-07	Wait 12h		350_Ti_8.0	5	350_Au_10.0	3		
450mm	450-EBL_Cr_20	None		8.0E-07	450_Cr_2.0	2						
450mm	450-EBL_Cr_50	None		8.0E-07	450_Cr_5.0	2						
450mm	450-EBL_Cr_100	None		8.0E-07	450_Cr_10.0	2						
450mm	450-EBL_Cr_200	None		8.0E-07	450_Cr_20.0	2						
450mm	450_[Ar-1]	Ar plasma	1	8.0E-07								
450mm	450_[Ar-1]_Cr-Au_50	Ar plasma	1	8.0E-07	450_Cr_5.0	2	450_Au_5.0	3				
450mm	450_[Ar-1]_Cr-Au_20-10	Ar plasma	1	8.0E-07	450_Cr_2.0	2	450_Au_1.0	3				
450mm	450_[Ar-1]_Ni_50	Ar plasma	1	8.0E-07	450_Ni_5.0	4						
450mm	450_[Ar-1]_Ti-Au_50	Ar plasma	1	8.0E-07	450_Ti_5.0	5	450_Au_5.0	3				
450mm	450_[Ar-1]_Ti-Cu_50	Ar plasma	1	8.0E-07	450_Ti_5.0	5	450_Cu_5.0	4				
450mm	450_[Ar-1]_Ti-Ni-Au_50	Ar plasma	1	8.0E-07	450_Ti_5.0	5	450_Ni_5.0	4	450_Au_5.0	3		
450mm	450_[O2]_Cr_50	O2 plasma	1	8.0E-07	450_Cr_5.0	2						
450mm	450_[O2]_Cr-Al_50	O2 plasma	1	8.0E-07	450_Cr_5.0	2	450_Al_5.0	1				
450mm	450_[O2]_Cr-Au_50	O2 plasma	1	8.0E-07	450_Cr_5.0	2	450_Au_5.0	3				
450mm	450_[O2]_Cr-Au_20-05	O2 plasma	1	8.0E-07	450_Cr_2.0	2	450_Au_0.5	3				
450mm	450_[O2]_Ti-Au_50	O2 plasma	1	8.0E-07	450_Ti_5.0	5	450_Au_5.0	3				
450mm	450_[O2]_Ti-Pt_50	O2 plasma	1	8.0E-07	450_Ti_5.0	5	450_Pt_5.0	6				
450mm	450_[O2]_Ti-Pt-Ti_50	O2 plasma	1	8.0E-07	450_Ti_5.0	5	450_Pt_5.0	6	450_Ti_5.0	5		
450mm	450_2x(Cr-Au)_50	None		8.0E-07	450_Cr_5.0	2	450_Au_5.0	3				
450mm	450_4x(Cr-Al-Cr)_50	None		8.0E-07	450_Cr_5.0	2	450_Al_5.0	1	450_Cr_5.0	2		
450mm	450_Ag_05	None		8.0E-07	450_Ag_0.5	3						

